



Phenol Formaldehyde Resin

NO.	Analysis Title	Specific Value	Method
1	PH	6.8-7	ISO 8975
2	M.P Range	83-84°c	ISO 31-46
3	FL.	43±1mm	ISO 8619
4	HEXA Cont.	9%	ISO 8988
5	Free Phenol	0.05%	ASTM D1312-93
6	B-Time	83-85 sec	ISO 8987
7	Ash	0	DIN 16945
8	Resin Cont.	97.4%	DIN 16945
9	Bulk Density (Dry)	0.48 gr/cm ³	ISO 60
10	Sieve analysis	94.2% (0.062 mm)	ISO 8620
11	Solubility Acetone		ISO 10080

Ahrar Chemistry ahrarchem.com

Email:Info@ahrarchem.com

Phone: +98 9122345678